

KBC122000 12V 200Ah



The Kaise cyclic batteries were developed for deep discharges with very heavy non-porous battery plates to withstand major discharging and charging cycles (deep cycle). These batteries use different chemistry combinations for the plates with active paste material and a slightly stronger than normal electrolyte, which allows for a much longer life in deep cycle applications.


Performance Characteristics

Nominal Voltage	12V		
Dimensions	Length (mm / inch)	522 / 20.55	
	Width (mm / inch)	238 / 9.37	
	Height (mm / inch)	218 / 8.58	
	Total Height (mm / inch)	223 / 8.78	
	Approx Weight	(Kg / lbs)	65 / 143.3
Design Life	10 years		
Terminal	M8		
Container Material	ABS		
Rated Capacity	189Ah / 18.9A	(10hr, 1.70V / cell, 25°C / 77°F)	
	118Ah / 11.8A	(1hr, 1.70V / cell, 25°C / 77°F)	
	81.75Ah / 327A	(15min, 1.70V / cell, 25°C / 77°F)	
Max. Discharge Current	1000A (5s)		
Internal Resistance	Approx 4.0mΩ		
Operating Temp. Range	Discharge : -15 ~ 55°C (5 ~ 131°F)		
	Charge : 0 ~ 40°C (32 ~ 104°F)		
	Storage : -15 ~ 40°C (5 ~ 104°F)		
Nominal Operating Temp. Range	25 ± 3°C (77 ± 5°F)		
Cycle Use	Initial Charging Current less than 40A		
	Voltage: 2.30VPC ~ 2.35VPC at 25°C (77°F)		
	Temp. Coefficient: -30mV/°C		
Standby Use	Initial Charging Current less than 40A		
	Voltage: 2.25VPC ~ 2.30VPC at 25°C (77°F)		
	Temp. Coefficient: -20mV/°C		
Capacity affected by Temperature	40°C (104°F)	103%	
	25°C (77°F)	100%	
	0°C (32°F)	86%	
Self Discharge	Fully charged Kaise Deep Cycle Series batteries may be stored for up to 6 months at 25°C (77°F) and then a freshening charge is required. For higher temperatures the time interval will be shorter.		

Discharge Constant Current (Amperes) at 77°F (25°C)

Volts/cell	15min	30min	1h	3h	5h	10h	20h
1.80V	261	182	112	50.5	35.2	18.7	10.0
1.75V	310	195	115	52.9	35.8	18.8	10.2
1.70V	327	201	118	54.5	36.4	18.9	10.4
1.60V	350	215	126	57.0	38.0	19.1	10.8

Dimensions and Terminal (Unit: mm (inches))



Applications

Solar power systems
Electric wheel chairs
Golf carts
Maritime equipment
Power plants
Railway systems
Telecommunications systems
Cable TV systems
Emergency power systems

Certifications

ISO 9001:2008 ISO 14001:2008



Discharge Current vs. Discharge Voltage


Final discharge voltage V/CELL	1.8	1.75	1.7	1.6
Discharge current (A)	$I \leq 0.1CA$	$0.25CA \geq I > 0.1CA$	$0.55CA \geq I > 0.25CA$	$I > 0.55CA$

Discharge Constant Power (Watts per cell) at 77°F (25°C)


Volts/cell	15min	30min	1h	2h	3h	5h
1.80V	538	355	212	125	97.0	69.0
1.75V	561	363	214	128	100	69.9
1.70V	569	373	218	132	104	70.8
1.60V	607	392	227	137	108	72.6

(Note) The above characteristics data are average values obtained within three charge/discharge cycles not the minimum values.


Charging Characteristics (standby use)




Self Discharge Characteristics




Temperature Effects in Relation to Battery Capacity



Temperature Effects on Float Life



Cycle Life in Relation to Depth of Discharge



IMPORTANT NOTE: The specifications presented herein are subject to revision without notice.

